



TECHNICAL DATA SHEET

VIA MASULLO 1^ TRAV.PRIVATA 80010-QUARTO-(NA)-ITALY
 TEL.+ 39 – 081 – 876.21.48 r.a. - FAX + 39 – 081 – 876.23.47
 www.dichemitaly.com E-mail: dichem@dichem.it

CODE: 36.315

ACRIMATT 2K/HS 4:1

DESCRIPTION

Transparent acrylic finish with matt effect (10 to 25 gloss). High solid, scratch-resistant with excellent yield and high resistance to yellowing.

PURPOSE

All types of refinishing after touching-up or complete respray on normal or metallic automotive colours.

BASIC DATA (At 25 deg. C - 50 % R. H.)

COVERAGE THEORETICAL

7,7 sqm/mixed litre (dft 50 um)

HARDENER

DILUENTE

Unihard 600 Standard or Fast

**MIXING RATIO BY VOLUME
4 : 1 : 10 > 20 %**

Diacril

POT-LIFE

2 hours

Acrimatt 2k/HS	volume 100 cc	by weight 100 gr
Unihard 600	25 cc	25 gr
Diacril	10/25 cc	10/25 gr

